



上海耐特 SHANGHAI NYTEX COMPOSITES
复合材料制品有限公司

TEL:021-59573168 FAX:021-59573707
http://www.nytex.com.cn

产品资讯

Product Information

NYLOY® NG-0215N

• 尼龙6 • 玻纤强化级 • 本色

性质	PROPERTY	测试方法 METHOD	单位 UNIT	结果(数据) RESULT
机械性能	MECHANICAL			
抗张强度	Tensile Strength	ASTM D638	kg/cm ² (MPa)	1050 (103.05)
断裂伸长率	Elongation	ASTM D638	%	2
抗折强度	Flexural Strength	ASTM D790	kg/cm ² (MPa)	1800 (176.65)
抗折弹性系数	Flexural Modulus	ASTM D790	kg/cm ² (MPa)	57000 (5593.86)
冲击强度	IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	4.5 (44.12)
	IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
硬度	Hardness Rockwell R Scale	ASTM D785	-	-
	Hardness Shore D	ASTM D2240	-	-
热性能	THERMAL			
热变形温度	Heat Deflection Temp	ASTM D648		
	(18.6kg/cm ²) (1.82MPa)		°C	-
	(4.6kg/cm ²) (0.46MPa)		°C	-
电气性能	ELECTRICAL			
耐电弧	Arc Resistance	ASTM D495	sec	-
CTI(溶液 A 型)	CTI,solution A	IEC 60112	-	-
其他性能	OTHER			
密度	Density	ASTM D792	g/cm ³	1.23
模收缩率 ⁽²⁾	Mold Shrinkage	ASTM D955	x10 ⁻³ mm/mm	-
含水率	Moisture Contents	-	%	-
耐燃性	Flammability	UL-94	1.6mm	-
		UL-94	3.2mm	-
附注	REMARK			
(1)本物性表为典型测试值, 仅供参考, 不作为正式质保承诺。				
(2)平行于流动方向的模收缩率, 测试试片尺 129×12.7×3.2mm。				